

Product Data Sheet
 Edition 18/08/2005
 Identification no:
 02 08 03 04 001 0 000013
 Sikafloor®-3 QuartzTop

Sikafloor®-3 QuartzTop

Coloured mineral dry shake floor hardener

Product Description

Sikafloor®-3 QuartzTop is a one part, preblended, coloured mineral dry shake hardener for concrete comprising of cement, specially selected quartz mineral aggregates, admixtures and pigments.

Uses

- Sikafloor®-3 QuartzTop provides a hard wearing, mineral dry shake topping for monolithic floors. When sprinkled and trowelled into fresh wet concrete floors, it forms a coloured, wear resistant smooth surface
- Typical uses are in warehouses, factories, shopping malls, public areas, restaurants and museums

Characteristics / Advantages

- Good wear resistance rating
- Impact resistance
- Cost effective surface hardener
- Dust proof
- Easy cleaning
- Increased resistance to oils and grease
- Quality assured factory blending
- Wide range of colours
- Suppresses fibers in concrete

Tests

Approval / Standards Conforms to the requirements of BS 8204, EN 206/1, ACI 304.1R 96 and TR 34

Product Data

Form

Appearance / Colours Powder
 Natural (concrete grey).
 Other colours upon request.

Packaging 25 kg bags

Storage

Storage Conditions / Shelf-Life 12 months from date of production if stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +30°C.



Technical Data

Chemical Base Natural mineral aggregates graded and mixed with cement, admixtures and pigments.

Density ~ 1.5 ± 0.1 kg/l (bulk density)

Layer Thickness ~ 2.5 to 3.0 mm at the recommended coverage of ~ 5.0 kg/m²

Mechanical / Physical Properties

Abrasion Resistance Class "AR2" High abrasion resistance (BS 8204 Part 2)
(Less than 0.2 mm wear depth)
UK Aston University, Report N^o: AL/AR 290598, dated 29.05.98
At least 4950 mg (UNE 48.250-92 / ASTM D-4060)
Taber Abrader H-22 / 1000 gr / 1000 cycles
GEOCISA Ref. P-02/01637 dated Jan. 9, 2003

System Information

System Structure Use products mentioned below as indicated in their respective Product Data Sheets.

Substrate: Fresh concrete slab (See Substrate Quality below)

Dryshake: Manual or machine application of Sikafloor[®]-3 QuartzTop
Levelling of surface by means of power trowel or laser screed.
Final smoothing with power trowel.

Curing compound: Application of any of the products in the Sikafloor[®] ProSeal or Sikafloor[®] ColourSeal range.

Application Details

Consumption ~ 5 kg/m². This figure does not allow for surface profile and wastage.

Substrate Quality The concrete deliveries must be of consistent quality.
A concrete slump in the range 75 to 110 mm will normally give best results.
The slab must be of good quality concrete with a minimum water/cement ratio consistent with the production of a fully compacted slab.
The compressive strength must be a minimum of 25 N/mm².
Use Sikament[®] or Sika Viscocrete[®] super plasticisers to ensure the optimum quality of concrete and, where fibres are used, their optimum dispersion within the mix.

Application Conditions / Limitations

Substrate Temperature +5°C min. / +35°C max.

Ambient Temperature +5°C min. / +35°C max.

Relative Air Humidity 30% r.h. min. / 98% r.h. max.

Application Instructions

Application Method / Tools

(i) Mechanical Application - Automatic spreader in conjunction with a laser screed:

Spread Sikafloor®-3 QuartzTop evenly onto the concrete immediately after screeding at 5 kg/m² in one application.

(ii) - Manual application:

Dependent on the conditions, remove the surface bleed water or allow it to evaporate. Sprinkle Sikafloor®-3 QuartzTop onto the screeded concrete evenly in 2 stages (first stage: 3 kg/m²; second stage: 2 kg/m²).

Care must be taken to apply the product without creating ripples etc. in the concrete surface. Overall application rate 5 kg/m². Casting Sikafloor®-3 QuartzTop powder carelessly or further than 2 metres from point of casting will reduce the consistency of finish.

Compaction:

The first application must be worked into the slab followed immediately by the application of the second stage quantity of Sikafloor®-3 QuartzTop.

Notes:

- Never add water to the surface where the dryshake has been applied.
- Sikafloor®-3 QuartzTop results in the slab surface becoming stiff more quickly than usual. Careful trimming must take place along the edges where adjoining slabs are to be poured.
- Final finishing to close pores and remove undulations can be achieved either by hand or powered trowel.

Cleaning of Tools

Clean all tools and application equipment with water immediately after use. Hardened/cured material can only be mechanically removed.

Application Time

Application time for dryshake products is influenced by every variable which affects the placing of concrete, and can therefore vary substantially, depending on the prevailing conditions.

For mechanical application with automatic spreader and laser screed, the spreading can start almost immediately after the concrete has been levelled to allow for the hydration of the dryshake. Compaction with the trowel can start as soon as the weight of the power trowels is supported by the concrete.

For manual application, the dryshake must be spread once the concrete can be stepped on, without leaving a print deeper than 3 - 5 mm.

Periodical checking of the condition and development of the concrete will determine the correct time frame for each stage and sequence of application.

Notes on Application / Limitations

The application of the dry shake powder must not be carried out in strong wind or in dry conditions.

Variations in concrete characteristics such as water content and cement may lead to slight colour variations.

Dry shake hardeners give a finish to concrete with some colour variation across the floor due to the natural variability of the concrete onto which they are applied.

To ensure optimum of colour consistency, it is essential that the floor laying operation is as clean and protected from the environment as possible.

Colour variation during the drying out period is normal for this system and is to be expected.

Every effort must be made to ensure an even application of Sikafloor®-3 QuartzTop. Correct timing and trowelling techniques are essential.

At low relative humidities (below 40%), efflorescence can appear on the surface.

At high relative humidities (above 80%), bleeding, slower curing and hardening can occur and extended finishing operations be required.

Slip resistance can be enhanced through chemical ageing. Refer to the Method Statement for Application for details.

Joints:

After finishing operations and completing saw cuts, clean off any residual saw lubricant / slurry without delay. Joints can be filled with Sikaflex® PRO-3WF or another appropriate Sikaflex® sealant in accordance with the floor design requirements.

Curing Details**Curing Treatment**

Cure and seal Sikafloor®-3 QuartzTop immediately after finishing using any of the products in the Sikafloor® ProSeal or Sikafloor® ColourSeal range. (Refer to separate Product Data Sheet).

Applied Product ready for use

Substrate temperature	+10°C	+20°C	+30°C
Foot traffic	~ 18 hours	~ 12 hours	~ 8 hours
Fully serviceable	~ 10 days	~ 7 days	~ 5 days

The above values are dependant upon the concrete reaching its design strength for serviceability and will be affected by changing ambient conditions, particularly temperature and relative humidity.

Cleaning / Maintenance**Methods**

To maintain the appearance of the floor after application, Sikafloor®-3 QuartzTop must have all spillages removed immediately and must be regularly cleaned using rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques, etc., using suitable detergents and waxes.

Notes

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult with Sika Ltd., China for the exact description of the application fields.

Health and Safety Information

Protective Measures Use of basic principles of industrial hygiene and protective clothing such as gloves and goggles etc. will enable this product to be used safely. Change soiled work clothes and wash hands before eating and after finishing work.

Local regulations and health and safety advice on packaging labels must be observed.

Ecology For the most current information please refer to the Material Safety Data Sheet available from Sika Ltd, China upon request.

Transportation Class For the most current information please refer to the Material Safety Data Sheet available from Sika Ltd, China upon request.

Important Notes Residues of material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.

Detailed health and safety information as well as detailed precautionary measures e.g. physical, toxicological and ecological data can be obtained from the material safety data sheet.

Toxicity For the most current information please refer to the Material Safety Data Sheet available from Sika Ltd, China upon request.

Legal Notes The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Guangzhou Ltd.
No. 96, JunDa Road,
Eastern Section, GET,
Guangzhou, P.R. China
Post Code: 510530
Tel: (86) 20 8226 6066
Fax: (86) 20 8226 6022
Email: marketing@cn.sika.com
Web-site: www.sika.cn

Sika (China) Ltd.
Suite 1602, Century Financial Tower,
No. 1 Suhua Road,
Suzhou Industrial Park,
Suzhou, Jiangsu, P.R. China
Post Code: 215021
Tel: (86) 512 6288 8997
Fax: (86) 512 6763 9897
Email: marketing@cn.sika.com

Sika Tianjin Branch
Xiaodongzhuang Town,
Jintang Road, Dongli District,
Tianjin, P.R. China
Post Code: 300300
Tel: (86) 22 2499 9598
Fax: (86) 22 2499 9728
Email: marketing@cn.sika.com

Sika Shanghai Office
Room 19BCD, Ou Jiang Building,
No. 768, Zhaajiang Road,
Shanghai, P.R. China
Post Code: 200030
Tel: (86) 21 6445 7003
Fax: (86) 21 6445 6745
Email: marketing@cn.sika.com

Sika Beijing Branch
Building 3, Section A,
Lightline Industry Garden Beijing
OPTO-Mechatronics Industrial Park
Post Code: 101111
Tel: (86) 10 8150 4888
Fax: (86) 10 8150 4111
Email: marketing@cn.sika.com

Sika Ltd., Dalian
No. 47, Gongxing Road,
Ganjingzi District,
Dalian, P.R. China
Post Code: 116031
Tel: (86) 411 8678 0060
Tel: (86) 411 8678 0070
Email: marketing@cn.sika.com



The product is manufactured under a HKQAA
ISO9001/ISO14001 certified quality/environmental
management system.